

Butyl Rubber Compounds



PRODUCT	DESCRIPTION	POLYMER	% SOLIDS +/- 3%	PERFORMANCE PROPERTIES 2 mils dry/ 2 mil PET film							CPS. RANGE	SOLVENT
				180° PEEL (Immediate)	180° PEEL (24 Hours)	180° PEEL (1 Week)	SHEAR 1" X 1" 4.4 LBS	SAFT 1/2" x 1/2" 200 grams	LOOP TACK (oz.)	PROBE TACK (grams)		
5006	Butyl PSA excellent cold temp	Buytl/SIS/SB	56	80	96	96	5 h 30 m	138	128	700	4000-8000	Heptane/Toluene
5005	Butyl PSA excellent cold temp	Buytl/SIS/SB	59	78	76	76	2h45m	128	80	650	4000-8000	Heptane/Toluene