

High Solids Tape Compounds



PRODUCT	DESCRIPTION	POLYMER	% SOLIDS +/- 3%	PERFORMANCE PROPERTIES 2 mils dry/ 2 mil PET film							CPS. RANGE	SOLVENT
				180° PEEL (Immediate)	180° PEEL (24 Hours)	180° PEEL (1 Week)	SHEAR 1" X 1" 4.4 LBS	SAFT 1/2" x 1/2" 200 grams	ROLLING Ball	PROBE TACK (grams)		
310	High viscosity cloth tape	Natural/SIS	71	50	50	50	45 m	108	1/2"	625	300,000-500,000	Heptane/Toluene
5124	All Purpose PSA	Natural/SIS	67	35	40	40	4 hr	118	11/2"	500	300,000-500,000	Heptane/Toluene
3126	High Viscosity cloth tape-soft	Natural/SIS	70	40	45	45	40 m	102	1/2"	600	150,000-250,000	Heptane/Toluene
610	High Viscosity cloth tape-low tack	Natural/SIS	70	65	65	65	4 hr 30m	116	1-Jan	550	250,000-350,000	Heptane/Toluene
364	High Viscosity latex free cloth	Polyisoprene/SIS	72	45	50	50	12 m	110	1"	600	350,000-450,000	Heptane/Toluene
2150	High Viscosity latex free cloth	Polyisoprene/SIS	66	150	150	150	15 m	118	31/2	1,000	150,000-250,000	Heptane/Toluene