

Latex Free Tape Compounds



PRODUCT	DESCRIPTION	POLYMER	% SOLIDS +/- 3%	PERFORMANCE PROPERTIES 2 mils dry/ 2 mil PET film							CPS. RANGE	SOLVENT
				180° PEEL (Immediate)	180° PEEL (24 Hours)	180° PEEL (1 Week)	SHEAR 1" X 1" 4.4 LBS	SAFT 1/2" x 1/2" 200 grams	LOOP TACK (oz.)	PROBE TACK (grams)		
9297	Soft, good adhesion to skin	Polyisoprene/SIS	69	80	85	90	5 m	100	64	600	250,000-350,000	Heptane/toluene
5145	Latex free PSA	Polyisoprene/SIS	69	140	140	140	10 m	106	110	700	250,000-400,000	Heptane/toluene
3643	Latex free PSA	Polioprene/SIS	69	95	100	100	60 m	118	84	700	250,000-400,000	Heptane/toluene
204	Latex free PSA stretch tapes	SIS/SBR	70	85	85	85	indefinite	188	80	550	75,000-225,000	Heptane/toluene
K-08-D	Latex free PSA stretch tapes	SIS	72	190	190	190	indefinite	184	240	1700	60,000-200,000	Toluene
5537	All purpose latex free PSA	SIS	45	100	100	105	indefinite	186	115	1,200	600-1200	Heptane/toluene
2150	Latex Free PSA	Polyisoprene/SIS	66	150	150	150	15 m	118	160	1,000	150000-250000	Heptane/toluene