

Heat Seal Adhesives



PRODUCT	DESCRIPTION	POLYMER	% SOLIDS +/- 3%	Performance Properties 3 mils on Cotton Sheeting						CPS. RANGE	SOLVENT
						Activation	Dwell				
3037	Firm, non-blocking, low temp	SBR	70%			200F	5 sec			250-400,000	Heptane
1235	Dry, high wet tack	SB/SBR	70%			240	5 sec			250-450,000	Heptane
3112	softer, high wet tack	SIS	70%			200	5 sec			250-450,000	Heptane
3025	softer, low temp	SBR	70%			180	5 sec			250-450,000	Heptane