

Removable Adhesives



PRODUCT	DESCRIPTION	POLYMER	% SOLIDS +/- 3%	PERFORMANCE PROPERTIES 2 mils dry/ 2 mil PET film							CPS. RANGE	SOLVENT
				180° PEEL (Immediate)	180° PEEL (24 Hours)	180° PEEL (1 Week)	SHEAR 1" X 1" 4.4 LBS	SAFT 1/2" x 1/2" 200 grams	LOOP TACK (oz.)	PROBE TACK (grams)		
7204	High Shear Removable	SBS	45	40	40	40	Indefinite	174	48	700	7000-11,000	Toluene
720	High Shear Removable	SBS	42	60	60	65	Indefinite	196	84	1,100	8000-12,000	Toluene
5025	High Shear Removable	Natural Rubber	40	60	65	65	Indefinite	180° F	64	900	120,000-150,000	Toluene
714	High Shear Removable	SBS	45	92	92	92	Indefinite	185	95	1,200	7000-11000	Toluene
219	High Tack Removable	SIS	63	124	136	136	Indefinite	206	152	1,500	30,000-45000	Heptane/Toluene