

Heat Seal Adhesives



PRODUCT	DESCRIPTION	CPS. Range	% SOLIDS	Activation Temp.	Dwell
3037	Firm, non-blocking, low temp	250,000 - 400,000	70	200	5 sec
1235	Dry, high wet tack	250,000 - 450,000	70	240	5 sec
3112	softer, high wet tack	250,000 - 450,000	70	200	5 sec
3025	softer, low temp	250,000 - 450,000	70	180	5 sec