

# Butyl Rubber Compounds



PRODUCT	DESCRIPTION	CPS. RANGE	% SOLIDS	180° PEEL (24 Hours) *	SHEAR 1" X 1" 4.4 LBS *	SAFT 1/2" x 1/2" 200 grams *	LOOP TACK (oz.) *	PROBE TACK (grams) *
5006	Butyl PSA excellent cold temp	2,500-5,500	65	90	8 Hours	163	120	700
5005	Butyl PSA excellent cold temp	9,000-15,000	59	90	6 Hours	164	80	650
529	PIB PSA	2,000-10,000	42	80	15 min	165	72	650
4015	PIB PSA	2,000-10,000	42	65	8 min	165	75	620